

PUB-NO: EP000698442A2
DOCUMENT-IDENTIFIER: EP 698442 A2
TITLE: Butt welding process using high density energy beam
PUBN-DATE: February 28, 1996

INVENTOR-INFORMATION:

NAME	COUNTRY
SAITO, YUJI	JP
MOUKO, MINORU	JP
SATO, MASAKAZU	JP

ASSIGNEE-INFORMATION:

NAME	COUNTRY
HONDA MOTOR CO LTD	JP

APPL-NO: EP95113193

APPL-DATE: August 22, 1995

PRIORITY-DATA: JP19704694A (August 22, 1994) .

INT-CL (IPC): B23K026/00, B23K033/00

EUR-CL (EPC): B23K026/26 ; B23K033/00

ABSTRACT:

CHG DATE=19990617 STATUS=O> First, welding protrusions of two aluminum alloy plates are butted against each other, and an engagement projection of one of the aluminum alloy plates is brought into engagement with an engagement recess of the other aluminum alloy plate, thereby maintaining the butted state and defining voids in back of butt regions of the welding protrusions in a direction of irradiation of a laser beam. Then, the laser beam is irradiated to the butt regions to bond the welding protrusions to each other. The Al2O3 films located on the surfaces of the welding protrusions on a back side in a direction of irradiation of the laser beam are pushed into the voids by a molten pool and hence, they cannot intrude into a weld zone to form a notch. By employing this arrangement in the butt welding using the laser beam, the need for a jig for maintaining the butted state of the aluminum alloy plates is eliminated and a butt joint having a high strength can be obtained. <MATH>